


FORTIDE®-WS

Product information



Two-component epoxy coating for use on wet surfaces.



Specific advantages:



For operating temperatures up to +80 °C (+176 °F).



Fulfils ISO21809-3, type 18-A.



Free from volatile solvents and isocyanates.



Can be applied to wet surfaces without time-consuming pre-treatment.



Coating of pipes under load is possible.

Product description

FORTIDE®-WS is a durable corrosion protection system for underground and submerged pipelines which has been specifically designed for use on **moist substrates**.

Moist surfaces often pose a particular challenge, especially when restoring old coatings on piping systems.

Its **special composition** means it provides a high-quality and safe coating even if a **condensate film**

has formed on a pipeline under load. The ability to apply it to wet surfaces **removes the need to disconnect the pipeline**, prevents long waiting times and therefore **significantly reduces costs**.

The isocyanate- and solvent-free system ensures **compliance with the most stringent environmental and health and safety requirements**.

FORTIDE®-WS fulfils the requirements of **ISO 21809-3, type 18A**.

The high-temperature resistance under specified mechanical load capacity forms the basis of a wide range of applications.

The coating's durability is a result of its excellent **resistance to cathodic disbondment** combined with **exceptional indentation strength**.

FORTIDE®-WS is available in different package sizes, which means that a practical and economical size is available for every project.

Typical product properties

Property	Unit	Typical value	Required value	Test method
Type	-	two components	-	ISO 21809-3
Colour	-	Black	-	
Recommended minimum layer thickness	µm	≥ 600	-	
Theoretical consumption for 600 µm DFT	kg/m ² l/m ²	0.87 0.62	-	
Indentation resistance (10 N/mm ² , stamp-∅ 1.8mm)	+80 °C (+176 °F) % of the original thickness	≤ 5	≤ 30	
Cathodic disbondment	+23 °C (+73 °F)	≤ 2	≤ 8	
	+80 °C (+176 °F)	≤ 6	≤ 15	
Hardness	+23 °C (+73 °F) Shore D	≥ 80	-	
Adhesion	EP on steel	≥ 14	≥ 10	
	EP on EP			
Adhesion after hot water immersion (28 d / +80 °C / +176 °F)	EP on steel	≥ 10	≥ 7	
	EP on EP	≥ 8	≥ 2	

Processing conditions

Ambient and substrate temperature approx.	+10 °C (+50 °F)	+20 °C (+68 °F)	+40 °C (+104 °F)	
Small package (Brush variant)	Pot life (250 g total mass)	approx. 1.5 h	approx. 35 min.	approx. 7 min.
	Tack-free	approx. 5 h	approx. 2.5 h	approx. 50 min.
	durable	approx. 24 h	approx. 9 h	approx. 3 h
Processing temperature	Substrate	≥ +10 °C (≥ +50 °F)		
	Environment	-40 °C to +50 °C (-40 °F to +122 °F)		
Steel surface	Degree of cleanliness (ISO 8501-1)	min. Sa 2 ½		
	surface roughness (ISO 8503-1)	40 – 100 µm		

Ordering information and packaging

Product name	Component (Packaging)	Contents per package approx.		Content per box
		[l]	[kg]	[pcs.]
FORTIDE®-WS 0.8 l Kit	Comp. A / B (cans)	0.6 / 0.2	0.95 / 0.2	12 / 12
FORTIDE®-WS 1.2 l Kit	Comp. A / B (cans)	0.9 / 0.3	1.4 / 0.3	8 / 8
FORTIDE®-WS	Comp. A / B (hobcock)	29 / 29	46 / 29	-
	Comp. A / B (barrel)	207 / 207	327 / 207	-

Storage

FORTIDE®-WS can be stored in its unopened original packaging for at least 12 months from the date of manufacture.

Storage temperature: +5 °C (+41 °F) to +30 °C (+86 °F).

Store in a dry and frost-free location.

DEKOTEC GmbH

Felderstrasse 24 | 51371 Leverkusen | Germany

Phone: +49 214 2602-0 | info@dekotec.com

www.dekotec.com

Our product information, application recommendations and other printed publications provide advice to the best of our knowledge and indicate our level of knowledge at the time of printing. The content is not legally binding. Therefore, no liability is assumed for incorrect and missing advice. The applicator is obliged to check the suitability and possibility of application for the intended purpose. Unless otherwise specified, all of the brands named are trademarks, at least registered in Germany, which are protected by law.

Only our general terms and conditions of sale, which you will find at www.dekotec.com, apply. This is a translation from the original German product information. In case of any discrepancy or any dispute arising on the interpretation, the German text of the respective German product information, shall be decisive. The legal relationship shall be governed by German law.

08.2023